



SAM MIX

SKIM COAT FINISH

面层腻子

SKIM COAT HALUS



QUIKPLASTER FINISH (SKIM COAT FINISH)

WHITE
(QF-W02)

GREY
(QF-G02)

- ✓ *Excellent adhesion*
- ✓ *Excellent workability*
- ✓ *Good water resistant*
- ✓ *Scratch resistant*
- ✓ *Non-toxic & non-corrosive*
- ✓ *Easy to mix and apply*

**Packaging Size :
25KG**

QUIKPLASTER BASE (SKIM COAT FINISH)

QUIKPLASTER FINISH (SKIM COAT FINISH) is a high quality polymer modified water-resistant cement-based thin plaster for finishing on wall and ceilings. It can be used on concrete and rendered surfaces to give a high quality plaster surface suitable for either painting or wallpapering.

QUIKPLASTER FINISH (SKIM COAT FINISH) 是一种高品质聚合物改性防水水泥基薄灰泥，用于墙壁和天花板的饰面，也可用于混凝土和渲染表面，以提供适用于油漆或墙纸的高质量石膏表面。

QUIKPLASTER FINISH (SKIM COAT FINISH) adalah plaster nipis berasaskan simen tahan air yang diubah suai polimer berkualiti tinggi untuk penamat di dinding dan siling. Ia juga boleh digunakan pada permukaan konkrit dan dirender untuk memberikan permukaan plaster berkualiti tinggi yang sesuai untuk lukisan atau kertas dinding.

Usage

1. Substrate must be dry, sound, flat / true & free of contaminants.
2. Do not use on painted surface.
3. Where necessary, dampen the dry concrete or rendered surfaces before application of **QUIKPLASTER FINISH (SKIM COAT FINISH)**.
4. Mix **QUIKPLASTER FINISH (SKIM COAT FINISH)** with water as per the recommended mix ratio. Mechanical mixing recommended.
5. Mix thoroughly for 3-5 minutes using mechanical mixer until homogeneous paste is achieved and lump free.
6. Allow mixture to stand for 5 minutes for additives to dissolve.
7. Re-mix if the mixture is left unattended for more than 30 minutes.
8. Apply by using a steel trowel or spatula.

Properties

Appearance	✓ White (QF-W02) ✓ Grey (QF-G02)
Binder	✓ OPC White Cement ✓ OPC Grey Cement
Filler Material	Calcium Carbonate Powder
Auxiliaries	Additives to enhance work-ability, water retention and adhesion
PH	12
Aggregate Size	0.5 mm max
Pot life	Approx. 2 hours
Coverage	Approx. 1.1KG/m ² /mm
Recommendation Thickness	1 - 2 mm per coat
Adhesion To Concrete	≥ 0.5 N/mm ² ≥ 1.0 N/mm ² ≥ 3.0 N/mm ²
- Tensile Test	
- Shear Adhesion	
- Comp. Strength	Chemically inert and non-toxic
Toxicity	
Mixing Ratio	Approx. 45% Water